



TECHNICAL DATA SHEET

Melinex™ Insulation – MEL0101AFR2 (Single Sided) Acrylic Flame Retardant – MEL1101AFR2 (Double Sided)

A flexible composite insulation composed of 10 mil type 339 DuPont Melinex™ with an acrylic thermosetting adhesive on one or both sides. The acrylic adhesive is b-staged and can bond with heat and pressure to many substrates. Melinex is a translucent white glossy film with similar properties to DuPont Mylar™.

PRODUCT ATTRIBUTES

- Excellent thermal stability, electrical properties, and chemical resistance
- High continuous temperature resistance
- Very thin profile
- RoHS compliant

REPRESENTATIVE PHYSICAL PROPERTIES		
PROPERTY	VALUE	TEST METHOD
NOMINAL THICKNESS , inches	0.012 - 0.014	ASTM D374
YIELD		
Square yards per pound	1.13	
Pounds per square yard	0.89	
DIELECTRIC STRENGTH , Volts (2-inch diameter electrodes)	17,000	ASTM D149
TENSILE STRENGTH		
Machine Direction (MD)	150 lbf	ASTM D882A
Cross Machine Direction (XMD)	210 lbf	
PEEL ADHESION (copper) , lbf: 90° Peel (German Wheel)	6, *Substrate Failure	
LAMINATION PARAMETERS		
Temperature , °F	310	
Time , minutes	30	
Pressure , psi	25 - 75	
CONTINUOUS USE TEMPERATURE , °C	150	

This product complies with RoHS (Restriction of Hazardous Substances) Directive, citation 2002/95/EC. Alamotape® does not manufacture this material using any of the banned substances listed in the directive guidelines as of July 1, 2008.

STORAGE

- Shelf life: one (1) year from date of shipment.
- Store in a clean area free from exposure to excessive heat, moisture or direct sunlight (50°F to 80°F).

Product performance will vary in each application and is dependent upon composite construction. Alamotape does not guarantee the replication of this data by third parties. None of the data or statements contained herein is intended to warrant the performance of this product. Data is representative and not intended as a manufacturing specification.