



A FLEXcon Holdings Company

Alamotape
6110 Rittiman Road
San Antonio, TX 78218
210.798.1900
800.549.9860
alamotape.com

TECHNICAL DATA SHEET

464NM21

Class H 180°C Insulation

A series of composites of type 464 Nomex® aramid fiber and electrical grade polyester film laminated with a high temperature adhesive system.

PRODUCT ATTRIBUTES

- Excellent thermal stability and conductivity
- Excellent mechanical properties
- Excellent electrical properties

REPRESENTATIVE PHYSICAL PROPERTIES		
PROPERTY	VALUE	TEST METHOD
NOMINAL THICKNESS, inches	0.003	ASTM D374
YIELD		
Square yards per pound	6.56	
Pounds per Square Yards	0.15	
DIELECTRIC STRENGTH (Volts - 2" electrodes)	5,000	ASTM D149
TENSILE STRENGTH (psi)		
Machine Direction (MD)	40	ASTM D828
Cross Machine Direction (XMD)	30	

STORAGE

- Shelf life: one (1) year
- Store in a clean area free from exposure to excessive heat, moisture or direct sunlight (50°F to 80°F).

Product performance will vary in each application and is dependent upon composite construction. Alamotape does not guarantee the replication of this data by third parties. None of the data or statements contained herein is intended to warrant the performance of this product. Data is representative and not intended as a manufacturing specification.